

HARDWAXOIL MAGIC SATIN



1L

5L

PRODUCT DESCRIPTION

Hardwax Oil based on natural, vegetable oils and waxes with exceptional wear resistance properties. When dry has a Satin sheen appearance. Good filling properties, natural colour, excellent chemical and mechanical resistance. Optional UA Hardener can be added at 5% for improved durabilities.

TECHNICAL DATA

VISCOSITY	45-55 SEC (DIN 4MM)
SOLID CONTENT	+/- 51% BY WEIGHT
DENSITY	+/-0.91 KG/L
GLOSS	SATIN
COLOR	CLEAR

CONFORM THE EUROPEAN DECO-PAINT DIRECTIVE 2010

USAGE

Particularly suitable for oiling of parquet, wooden floors and Furniture. Gives the wood a natural appearance and is easy to repair. It is advisable to apply thin layers. Multiple layers increase the gloss.

PREPARATION

Sand the surface using a 100-120 grit sandpaper and remove sanding dust before application.

USER TIPS

Before use, shake and stir well. Can be applied by polishing machine (white or beige pad), paintbrush, roller or cloth. After applying the oil, the excess has to be buffed in until the surface doesn't feel sticky. At least 2 coats are recommended for hard wood. For soft wood 3 coats are recommended. For industrial use, please contact our service centre.

TIP: an oil retarder Ciranova can be added to extend the open time.



DRYING TIMES

Can be overcoated after 6 to 8 Hours. The drying time is very dependent on the quantity applied, the temperature and air ventilation in the room. In higher temperatures and better ventilated rooms the drying times will be reduced.



APPLYING QUANTITY

25-30 m²/liter per coat

AFTER TREATMENT

Clean regularly with flooringsoap Ciranova. Depending on the use of the floor, use maintenance oil 1 time a year. For thorough cleaning, use Intensive Cleaner Ciranova[®].

ATTENTION: The hardwaxoil needs +/- 14 days to fully cure. Don't use any water or maintenance products on the floor during this period.

PRODUCT INFORMATION

Shelf life: up to 2 year in a well closed original packaging.

SPECIAL QUALITIES

Used cloths or pads should be plunged in water because of the danger of spontaneous combustion. We recommend Hardwaxoil Magic SATIN as topcoat on the pigmented Hardwaxoils.

Colored Hardwaxoils should always be tested before treating the entire surface. Used sanding grain, type of wood,may affect the final colour. To clean the used tools you can use the Cleaning Thinner Ciranova.

Ciranova[®] products are made for the professional user. The instructions specified in the data sheet are formulated after necessary tests were performed and after years of experience. However, they are drawn to our best knowledge and ability. The user must test the application of the product in the for him applicable conditions. Guarantee can not be derived out the text of this technical description.

PRODUCED BY DEBAL COATINGS NV

Industrieweg 29 – B 8800 Beveren-Roeselare
tel +32 (0) 51 30 11 40 fax +32 (0) 51 31 26 48
www.ciranova.be ciranova@ciranova.be