

# ECOFIX



5L 1L

As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

### Produced by Debal Coatings nv

Industrieweg 29 - 8800 Beveren-  
Roeselare Belgium tel. +32 (0) 51 30 11 40  
fax +32 (0) 51 31 26 48  
ciranova@ciranova.be

Versie / version : 04/2016

### PRODUCT DESCRIPTION

Water based impregnation oil for parquet and wooden furniture. The wood retains its original and untreated appearance. Only for interior and domestic use.

### TECHNICAL DATA

Viscosity	+/- 20 sec. (Din 4mm/20°C)
SOLID CONTENTS	+/- 25 % by weight
DENSITY	+/- 1,00 kg/lt.
Gloss	<b>matt</b>
NMP FREE	
CONFORM THE EUROPEAN DECO-PAINT DIRECTIVE 2010	

### PREPARATION

Surface: Solid wood, ingeneerd wood. Sand the surface with grain 100-150 and afterwards remove sanding dust.

### USER TIPS

ECOFIX can be used both as a sealer and topcoat. Mix the product well before use. After mixing or stirring the product, the product have to rest for 15 minutes before use. Application is done by a brush or roller.

Apply the first coat wet in wet to avoid overlapping. When the first layer is dry, apply the second layer as the first layer. When the second layer is dry, sand with grain 150-180, remove sand dust and apply the third layer.



### DRYING TIMES

Dust free: after 20 to 30 minutes  
Sandable: after 4 to 6 hours  
Chargeable after 24 hours

The drying is strongly depending on the applied quantity, the temperature, air humidity and the ventilation of the room. Through a higher temperature and a good ventilation, drying time is limited.



### APPLYING QUANTITY

10 - 12 m<sup>2</sup>/lt.

### AFTERTREATMENT

- Use Hard floor fresh Ciranova for regular maintenance.
- Use UNICARE X-MATT for periodic maintenance.
- Ecofix can also be finished with OCULTO or FORTICO

### PRODUCT INFORMATION

12 months in the original and unopened packaging.  
Warehousing at between 5°C and 40°C - not frost-durable.

### SPECIAL QUALITIES

Use only stainless material. After use, since the material directly with water. This product cannot be poured into sewerage. If a stain on the wood is needed, only use AQUAPAD + hardener Ciranova. Be aware of discoloration or detachment because of wood compounds like resins or tannin.