











| DESCRIPTION | | | |
|--|---|-------------|---|
| Total thickness | EN ISO 24346 | mm | 2.5 |
| Backing | - | - | Jute fabric |
| Weight | EN ISO 23997 | g/sqm | 3000 |
| Width of sheet | EN ISO 24341 | cm | 200 |
| Length of sheet | EN ISO 24341 | m | 20 - 31 |
| Material content | 98% natural materials (bio-based and mineral) : linseed oil, wood flour, resins, cork, minerals, jute fabric, among which 74% are rapidly renewable. 100 % recyclable, contains up to 40 % recycled material. | | |
| CLASSIFICATION | | | |
| Norm / Product specification | - | - | EN ISO 24011 |
| European classification | EN ISO 10874 | class | 23 / 34 / 43 |
| Fire rating | EN 13501-1 | class | Cfl-s1* |
| Slip resistance | ASR A1.5 /DIN 51130 – BGR 181 | class | R9 |
| Impact sound insulation | EN ISO 717-2 | dB | 3 dB |
| PERFORMANCES | | | |
| Residual indentation | EN ISO 24343-1 | mm | ≤ 0.15 |
| Colour fastness | EN ISO 105 - B02 | degree | ≥6 |
| Vertical resistance | EN 1081 | Ohm | $1 \times 10^6 \leq R \leq 1 \times 10^8$ |
| Point contact resistance | VDE 0100 | kOhm | >100 |
| Static electrical propensity | EN 1815 | kV | < 2.0 |
| Castor chair test (Type W) | ISO 4918 | - | OK |
| Thermal resistance | EN 12667 | Sqm,K/ W | 0.015 |
| Thermal conductivity | EN ISO 10456 | W/(m.K) | 0.17 |
| Surface treatment | - | - | LPX |
| Chemical products resistance | EN ISO 26987 | class | OK |
| Anti-bacterial activity (E. coli – S. aureus – MRSA)** | EN ISO 22196 (JIS Z 2801) | - | > 99,99% inhibits growth after 24h |
| CERTIFICATES AND LABELS | | | |
|      | | | |
| CE MARKING | | | |
|  | EN 14041 : 2004 AC : 2006 | - |     |

* Glued according to certificate.

DOP numbers available from your local branch.



Depending on light exposure, the product color can vary, due to linoleum natural oxidization process. The process is reversible.

We recommend that the samples be exposed to sunlight for several hours prior to making a final color choice